

Journal of the Facultad de Minas, Universidad Nacional de Colombia - Medellin Campus



DYNA 85 (206), September, 2018 - ISSN 0012-7353 Tarifa Postal Reducida No. 2014-287 4-72 La Red Postal de Colombia, Vence 31 de Dic. 2018.







DYNA is an international journal published by the Facultad de Minas, Universidad Nacional de Colombia, Medellín Campus since 1933. DYNA publishes peer-reviewed scientific articles covering all aspects of engineering. Our objective is the dissemination of original, useful and relevant research presenting new knowledge about theoretical or practical aspects of methodologies and methods used in engineering or leading to improvements in professional practices. All conclusions presented in the articles must be based on the current state-of-the-art and supported by a rigorous analysis and a balanced appraisal. The journal publishes scientific and technological research articles, review articles and case studies.

DYNA publishes articles in the following areas:

Organizational Engineering Civil Engineering Materials and Mines Engineering Geosciences and the Environment Systems and Informatics Chemistry and Petroleum Mechatronics Bio-engineering Other areas related to engineering

### **Publication Information**

DYNA (ISSN 0012-73533, printed; 2346-2183, online) is published by the Facultad de Minas, Universidad Nacional de Colombia, with a bimonthly periodicity (February, April, June, August, October, and December). Circulation License Resolution 000584 de 1976 from the Ministry of the Government.

### **Contact information**

Web page:http://dyna.unalmed.edu.coE-mail:dyna@unal.edu.coMail address:Revista DYNAFacultad de MinasUniversidad Nacional de Colombia -<br/>Medellín CampusCarrera 80 No. 65-223 Bloque M9 - Of.:107Telephone: (574) 4255068 Fax: (574) 4255343Medellín - Colombia

### © Copyright 2016. Universidad Nacional de Colombia

The complete or partial reproduction of texts with educational ends is permitted, granted that the source is duly cited. Unless indicated otherwise.

### Notice

All statements, methods, instructions and ideas are only responsibility of the authors and not necessarily represent the view of the Universidad Nacional de Colombia. The publisher does not accept responsibility for any injury and/or damage for the use of the content of this journal.

The concepts and opinions expressed in the articles are the exclusive responsibility of the authors.

### Institutional Exchange Request

DYNA may be requested as an institutional exchange through the e-mail canjebib\_med@unal.edu.co or to the postal address:

Biblioteca Central "Efe Gómez" Universidad Nacional de Colombia, Sede Medellín Calle 59A No 63-20 Teléfono: (57+4) 430 97 86 Medellín - Colombia

### **Indexing and Databases**

DYNA is admitted in:

The National System of Indexation and Homologation of Specialized Journals CT+I-PUBLINDEX, Category A1

Science Citation Index Expanded Web of Science - WoS, Thomson Reuters Journal Citation Reports - JCR SCImago Journal & Country Rank - SJR Science Direct SCOPUS **Chemical Abstract - CAS** Scientific Electronic Library on Line - SciELO GEOREF PERIÓDICA Data Base Latindex Actualidad Iberoaméricana RedALyC - Scientific Information System Directory of Open Acces Journals - DOAJ PASCAL CAPES UN Digital Library - SINAB CAPES **EBSCO Host Research Databases** 

### **Publisher's Office**

Juan David Velásquez Henao, Director Mónica del Pilar Rada T., Editorial Coordinator Catalina Cardona A., Editorial Assistant Amilkar Álvarez C., Diagrammer Byron Llano V., Editorial Assistant Landsoft S.A., IT

### **Reduced Postal Fee**

Tarifa Postal Reducida # 2014-287 4-72. *La Red Postal de Colombia,* expires Dec. 31st, 2018



SEDE MEDELLÍN Facultad de minas

# DYNA





DYNA http://dyna.medellin.unal.edu.co/

COUNCIL OF THE FACULTAD DE MINAS Dean

Verónica Botero Fernández, PhD

Vice-Dean Eliana Isabel Arango Zuluaga, PhD

Vice-Dean of Research and Extension Juan Fernando Ramírez Patiño, PhD

Director of University Services Santiago Medina Hurtado, PhD

Academic Secretary Lina María Gómez Echavarría, PhD

Representative of the Curricular Area Directors Cesar Javier Vinasco Vallejo, PhD

Representative of the Curricular Area Directors Bibian Alonso Hoyos Madrigal, PhD

Representative of the Basic Units of Academic-Administrative Management Femando Jesús Guevara Carazas, PhD

Representative of the Basic Units of Academic-Administrative Management Andres Osorio Arias, PhD

Professor Representative Miguel David Rojas López, PhD

Delegate of the University Council León Restrepo Mejía, PhD

Student representative undergraduate at the Faculty Council Luis Miguel Gómez Zuluaga

### FACULTY EDITORIAL BOARD

Dean Verónica Botero Fernández, PhD

Vice-Dean of Research and Extension Juan Fernando Ramírez Patiño, PhD

Members Oscar Jaime Restrepo Baena, PhD Juan David Velásquez Henao, PhD Jaime Aguirre Cardona, PhD Alfonso Espinosa Parada, PhD Mónica del Pilar Rada Tobón, MSc

### JOURNAL EDITORIAL BOARD Editor-in-Chief

Juan David Velásquez Henao, PhD Universidad Nacional de Colombia, Colombia

Editors George Barbastathis, PhD Massachusetts Institute of Technology, USA

Tim A. Osswald, PhD University of Wisconsin, USA

Juan De Pablo, PhD University of Wisconsin, USA

Hans Christian Öttinger, PhD Swiss Federal Institute of Technology (ETH), Switzerland

Patrick D. Anderson, PhD Eindhoven University of Technology, the Netherlands

Igor Emri, PhD Associate Professor, University of Ljubljana, Slovenia

Dietmar Drummer, PhD Institute of Polymer Technology University Erlangen-Nürnberg, Germany

Ting-Chung Poon, PhD Virginia Polytechnic Institute and State University, USA

Pierre Boulanger, PhD University of Alberta, Canadá

Jordi Payá Bernabeu, Ph.D. Instituto de Ciencia y Tecnología del Hormigón (ICITECH) Universitat Politècnica de València, España

Javier Belzunce Varela, Ph.D. Universidad de Oviedo, España

Luis Gonzaga Santos Sobral, PhD Centro de Tecnología Mineral - CETEM, Brasil

Agustín Bueno, PhD Universidad de Alicante, España

Henrique Lorenzo Cimadevila, PhD Universidad de Vigo, España

Mauricio Trujillo, PhD Universidad Nacional Autónoma de México, México Carlos Palacio, PhD Universidad de Antioquia, Colombia

Jorge Garcia-Sucerquia, PhD Universidad Nacional de Colombia, Colombia

Juan Pablo Hemández, PhD Universidad Nacional de Colombia, Colombia

John Willian Branch Bedoya, PhD Universidad Nacional de Colombia, Colombia

Enrique Posada, Msc INDISA S.A, Colombia

Oscar Jaime Restrepo Baena, PhD Universidad Nacional de Colombia, Colombia

Moisés Oswaldo Bustamante Rúa, PhD Universidad Nacional de Colombia, Colombia

Hernán Darío Álvarez, PhD Universidad Nacional de Colombia, Colombia

Jaime Aguirre Cardona, PhD Universidad Nacional de Colombia, Colombia









DYNA 85 (206), September, 2018. Medellin. ISSN 0012-7353 Printed, ISSN 2346-2183 Online

### **CONTENTS**

| 9   | Electrochemical analysis of the degradation of nitrided zirconia 3Y-TZP<br>Kevin Dorado-Bustamante, Sara Leal-Marin & Hugo Estupiñán-Duran  |
|-----|---|
| 16  | Dynamic adjustment of a MLFQ flow scheduler to improve cloud applications performance<br>Sergio Armando Gutiérrez, Marinho Barcellos & John Willian Branch  |
| 24  | Use of BOF slag and blast furnace dust in asphalt concrete: an alternative for the construction of pavements<br>Alfonso López-Díaz, Ricardo Ochoa-Díaz & Gloria Elizabeth Grimaldo-León   |
| 31  | Impact on the direct costs of social interest and priority interest housing by including new construction standards: Cali case<br>Mauricio Chávez-Calle, Diego Darío Pérez-Ruiz & María Fernanda Serrano-Guzmán                                     |
| 39  | The use of GS1 standards to improve the drugs traceability system in a 3PL Logistic Service Provider<br>Igor Lopes-Martínez, Lianet Paradela-Fournier, Janett Rodríguez-Acosta, Jenny Laura Castillo-Feu, Martha I. Gómez-Acosta & Alegna Cruz-Ruiz |
| 49  | Development of a parametric cable driven planar robot<br>Juan Pablo Castrillón-Restrepo, Sebastián Jiménez-Gómez & Federico Saldarriaga-Ángel   |
| 59  | Effect of fly ash and silica fume on rheology, compressive strength and self-compacting in cement mixtures<br>Jaime Arturo Correa-Yepes, Nestor Rojas-Reyes, Jorge I. Tobón   |
| 69  | Using a non-reducing sugar in the green synthesis of gold and silver nanoparticles by the chemical reduction method<br>Wilson Agudelo, Yuliet Montoya & John Bustamante   |
| 79  | Levelized avoided cost of electricity model based on power system operation<br>Cristian Camilo Marín-Cano & Diego Adolfo Mejía-Giraldo  |
| 85  | Heavy metal contribution by runoff in a high-altitude megacity: a method based on the road-deposited sediment characterization<br>Carlos Zafra-Mejía, Hugo Rondón-Quintana & Álvaro Gutiérrez-Malaxechebarria                                       |
| 95  | Design, development, and implementation of an assistive technology device for shoulder telerehabilitation via the Internet<br>Cristian D. Chamorro-R., Gladys Caicedo-D. & Jose I. Garcia-M.  |
| 105 | Productive process improvement to elaborate cane train baskets, using Coloured Petri nets<br>Jesus Filander Caratar-Chaux, Ruth Edmy Cano-Buitrón & José Isidro Garcia-Melo   |
| 114 | Active geodetic network: application in topography<br>Enrique Cano-Jódar, Manuel Sánchez-de la Orden & Javier Mesas-Carrascosa  |
| 121 | Application of OpenFoam solver SettlingFoam to bedload sediment transport analysis<br>Verónica Carrillo-Serrano & Esteban Pacheco-Tobar   |
| 128 | Encapsulation of β-carotene extracted from peach palm residues: A stability study using two spray-dried processes<br>Luis Eduardo Ordoñez-Santos, Jader Martínez-Girón & Rafael Humberto Villamizar-Vargas  |
| 135 | Svnergistic effects in anaerobic codigestion of chicken manure with industrial wastes<br>Liliana del Pilar Castro-Molano, Humberto Escalante-Hernández, Luis Enrique Lambis-Benítez & José Daniel Marín-Batista                                     |
| 142 | Palladium nanoparticles from a surfactant-modified hydroxysalt exchanged with tetrachloropalladate<br>Maby Mool Martínez, Rogelio Ocampo-Cardona, Jhon Mauricio Aguirre-Cortés, Oscar Giraldo & Luz Amalia Ríos-Vásquez                             |
| 148 | Morphological and nanomechanical characterization of Guadua Angustifolia kunth fiber by means of SEM and AFM<br>Martin Eduardo Espitia-Nery, Dery Esmeralda Corredor-Pulido, Nelson Javier Rodríguez-Ramírez & Jeimy Natalia Calderón-Bustos        |
| 155 | Kinetic parameters of lactic acid bacterial isolated from fermented milk "Suero Costeño"<br>Francia Elena Valencia-García, Karina Edith Motato-Rocha, Madalyd Yurani Vera-Peña & Martha Liliana Sepúlveda-Lindarte                                  |
| 162 | Soft Pre-stressed PET Profiles as reinforcing fibers in structural elements made of concrete<br>Sergio Márquez-Domínguez, Edgar Mejía-Sánchez, Jesús Antonio Arenzano-Altai, Gerson Omar Martínez-Guevara & Dante Tolentino                         |
| 171 | Entropy and negentropy of private electric vehicles in urban systems: homeostasis of mobility in Mexico<br>Mario Guadalupe González-Pérez   |
| 178 | Structural, thermal, rheological, morphological and mechanical properties of thermoplastic starch obtained by using hyperbranched polyester<br>polyol as plasticizing agent<br>Manuel Guzmán & Edwin A. Murillo                                     |
| 187 | An evaluation of the controlled release of ammoniacal nitrogen from residual cellulose/polyvinyl alcohol hydrogels as an alternative to traditional fertilization processes   |
|     | Marypei Montoya-Alvarez, Adriana Maria Quinchia-Figueroa, Octavio Gonzalez-Murillo & Pedronel Araque-Marin<br>Design of metacognitive expectations of cognitive functions through ontological representations                                       |

- 194 Dalia P. Madera-Doval, Manuel F. Caro-Piñeres, Adán A. Gómez-Salgado, Ana M. Cardozo-Soto & Jovani A. Jiménez-Builes
  - Simulation-optimization techniques for closed-loop supply chain design with multiple objectives
    - 202 William Javier Guerrero, Laura Andrea Sotelo-Cortés & Enrique Romero-Mota
      - Site characterization of a tropical soil by in situ tests 211
        - Breno Padovezi Rocha & Heraldo Luiz Giacheti





- Sugarcane molasses and vinasse as a substrate for polyhydroxyalkanoates (PHA) production Alejandro Acosta-Cárdenas, Wilman Alcaraz-Zapata & Mariana Cardona-Betancur
- Evaluation of water use in food SMEs: Case study of a poultry processing plant in Colombia Yelitza Angélica Zorrilla-Ortega, Juan Pablo Silva, Valentina Prado & Pablo César Manyoma 226
  - Nutrient losses due to water erosion using simulated rainfall in southern Brazil
- Jeane Cruz Portela, Neroli Pedro Cogo, Jacques Carvalho Ribeiro Filho, Letícia Sequinatto, Rafael Oliveira Batista, Carolina Malala Martins Souza & Joaquim Emanuel Fernandes Gondim
  - Teratogenic effect on bone tissue development in Rattus norvegicus Wistar strain, induced by the presence of arsenic Mirava Quitario Páraz, Juan Carlos Gavián Quarzín, Alberto, José Cordillo Martínez & Francisco Prieto Carcía
    - Mireya Quiterio-Pérez, Juan Carlos Gaytán-Oyarzún, Alberto José Gordillo-Martínez & Francisco Prieto-García 242
      - Design and Calculation of a Hybrid Solar-Hydraulic Power Station in Gran Canaria Abian Beltrán, Herberth Gracia-León, Daniella Rodríguez-Urrego & Leonardo Rodríguez-Urrego 250
      - Electrocoagulation of indigo carmine dve solution with magnesium and AZ31 allov anodes
- Dayana Donneys-Victoria, Cristian Camilo Ospina-Toro, Mónica Vanesa Zapata-Villegas, Nilson Marriaga-Cabrales, Fiderman Machuca-Martínez, Juan M. Peralta-Hérnandez & Carlos A. Martínez-Huitle
  - Integrating SOA and MAS in intelligent environments Manuel Sánchez, Jose Aguilar & Ernesto Exposito 268
  - A planning algorithm in a class of discrete event systems
  - Guelvis Mata, Bladismir Ruiz, Claudia Camacho, Arnaldo Méndez, Sergio Muñoz & Hicher Zambrano
  - Agronomic and environmental benefits of nitrogen fertilizers sources in Ocimum basilicum L Martha Constanza Daza-Torres, Greydy Selene Ladino-Tabarquino & Norberto Urrutia-Cobo
  - Risk assessment in water treatment processes for the development of a Water Safety Plan WSP
    - Andrea Pérez-Vidal, Juan Carlos Escobar-Rivera & Patricia Torres-Lozada Design of a serious emerging games engine based on the optimization algorithm of ant colony
    - Jose Aguilar, Junior Altamiranda & Francisco Díaz
  - Palladium nanoparticles from a surfactant-modified hydroxysalt exchanged with tetrachloropalladate
  - Heiner Alexander Vargas-Perea, Robinson Rocha-González, Mónica Andrea Botero-Londoño, Alexander Sepúlveda & Clara Lilia Calderón-Triana Estimación del retroceso glaciar en los volcanes Nevado del Ruiz, Tolima y Santa Isabel, Colombia a través de imágenes ópticas y Din-SAR Mario Fernando Monterroso-Tobar, Jhon Makario Londoño-Bonilla & Sergey Samsonov
    - Caracterización de residuos de demolición y construcción para la identificación de su potencial de reúso Lina María Chica-Osorio & Juan Manuel Beltrán-Montoya 338
      - Relationship between the particle size and the crystalline phases amount of an aluminum dross
        - Adriana Gómez-Gómez, Luz Elena Vinasco, Nelson Batista de Lima & Jorge Aberto Soares Tenório 348



Our cover Image alluding to Article: Morphological and nanomechanical characterization of Guadua Angustifolia kunth fiber by means of SEM and AFM

### Authors:

Martin Eduardo Espitia-Nery, Dery Esmeralda Corredor-Pulido, Nelson Javier Rodríguez-Ramírez & Jeimy Natalia Calderón Bustos





DYNA 85 (206), September, 2018. Medellin. ISSN 0012-7353 Printed, ISSN 2346-2183 Online

### **CONTENIDO**

- Análisis electroquímico de la degradación de circonia 3Y-TZP nitrurada 9
  - Kevin Dorado-Bustamante, Sara Leal-Marin & Hugo Estupiñán-Duran
- Ajuste dinámico de un programador de flujos MLFQ para mejorar el desempeño de aplicaciones en la nube 16
  - Sergio Armando Gutiérrez, Marinho Barcellos & John Willian Branch
- Uso de escoria BOF y polvo de alto horno en concretos asfálticos: una alternativa para la construcción de pavimentos 24 Alfonso López-Díaz, Ricardo Ochoa-Díaz & Gloria Elizabeth Grimaldo-León
- Impacto en costos directos de vivienda de interés social y de interés prioritario por inclusión de nuevas normas de construcción: caso Cali 31 Mauricio Chávez-Calle, Diego Darío Pérez-Ruiz & María Fernanda Serrano-Guzmán
  - Uso de los estándares GS1 para la mejora del sistema de trazabilidad de medicamentos en un operador logístico 3PL 39 Igor Lopes-Martínez, Lianet Paradela-Fournier, Janett Rodríguez-Acosta, Jenny Laura Castillo-Feu, Martha I. Gómez-Acosta & Alegna Cruz-Ruiz
    - Desarrollo de un robot cartesiano parametrizable comandado por cables 49 Juan Pablo Castrillón-Restrepo, Sebastián Jiménez-Gómez & Federico Saldarriaga-Ángel
- Efecto de las cenizas volantes y el humo de sílice sobre la reología, resistencia a la compresión y autocompactación en mezclas de cemento 59 Jaime Arturo Correa-Yepes, Nestor Rojas-Reyes, Jorge I. Tobón
  - Uso de una azúcar no reductora en la síntesis verde de nanopartículas de oro y plata por medio de reducción química 69 Wilson Agudelo, Yuliet Montoya & John Bustamante
    - Modelo de costo evitado nivelado de electricidad basado en la operación del sistema de potencia 79 Cristian Camilo Marín-Cano & Diego Adolfo Mejía-Giraldo
- Contribución de metales pesados por escorrentía en una megaciudad de elevada altitud: un método basado en la caracterización del sedimento vial 85
  - Carlos Zafra-Mejía, Hugo Rondón-Quintana & Álvaro Gutiérrez-Malaxechebarria
  - Diseño, desarrollo e implementación de una ayuda tecnológica para rehabilitación de hombro tele-operada vía Internet 95 Cristian D. Chamorro-R., Gladys Caicedo-D. & Jose I. Garcia-M.
    - Mejora del proceso productivo para elaborar canastas para trenes cañeros, utilizando redes de Petri coloreadas 105 Jesus Filander Caratar-Chaux, Ruth Edmy Cano-Buitrón & José Isidro Garcia-Melo
      - Red geodésica activa: aplicación en topografía 114
      - Enrique Cano-Jódar, Manuel Sánchez-de la Orden & Javier Mesas-Carrascosa
  - Aplicación del solucionador SettlingFoam de OpenFoam para el análisis del transporte de sedimento de carga de lecho 121 Verónica Carrillo-Serrano & Esteban Pacheco-Tobar
- Encapsulación de β-caroteno extraído a partir de residuos de chontaduro: Un estudio de estabilidad usando dos procesos de secado por atomización 128
  - Luis Eduardo Ordoñez-Santos, Jader Martínez-Girón & Rafael Humberto Villamizar-Vargas
  - Efectos sinérgicos en la codigestión anaerobia de gallinaza y residuos industriales 135 Liliana del Pilar Castro-Molano, Humberto Escalante-Hernández, Luis Enrique Lambis-Benítez & José Daniel Marín-Batista
  - Nanopartículas de paladio a partir de una hidroxisal modificada con surfactante intercambiada con tetracloropaladato
    - 142 Maby Mool Martínez, Rogelio Ocampo-Cardona, Jhon Mauricio Aguirre-Cortés, Oscar Giraldo & Luz Amalia Ríos-Vásquez
    - Caracterización morfológica y nanomecánica de la fibra de Guadua Angustifolia kunth mediante SEM y AFM 148 Martin Eduardo Espitia-Nery, Dery Esmeralda Corredor-Pulido, Nelson Javier Rodríguez-Ramírez & Jeimy Natalia Calderón-Bustos
      - Parámetros cinéticos de bacterias ácido-lácticas aisladas de la leche fermentada "Suero Costeño" 155 Francia Elena Valencia-García, Karina Edith Motato-Rocha, Madalyd Yurani Vera-Peña & Martha Liliana Sepúlveda-Lindarte
    - Perfiles de PET ligeramente pretensados como fibras de refuerzo en elementos estructurales de concreto 162 Sergio Márquez-Domínguez, Edgar Mejía-Sánchez, Jesús Antonio Arenzano-Altai, Gerson Omar Martínez-Guevara & Dante Tolentino
  - Entropía y negentropía del vehículo eléctrico particular en sistemas urbanos: homeostasis de la movilidad en México 171 Mario Guadalupe González-Pérez
  - Propiedades térmicas, reológicas, morfológicas y mecánicas de almidón termoplástico obtenido usando un poliéster poliol altamente ramificado como agente plastificante 178
    - Manuel Guzmán & Edwin A. Murillo
  - Evaluación de la liberación controlada de nitrógeno amoniacal a partir de un hidrogel de celulosa residual/polivinil alcohol como una alternativa a los procesos de fertización tradicionales 187
    - Marybel Montoya-Álvarez, Adriana María Quinchía-Figueroa, Octavio González-Murillo & Pedronel Araque-Marín
    - Diseño de expectativas metacognitivas de funciones cognitivas a través de representaciones ontológicas 194 Dalia P. Madera-Doval, Manuel F. Caro-Piñeres, Adán A. Gómez-Salgado, Ana M. Cardozo-Soto & Jovani A. Jiménez-Builes
    - Técnicas de simulación-optimización para el diseño de cadenas de abastecimiento de ciclo cerrado con múltiples objetivos 202 William Javier Guerrero, Laura Andrea Sotelo-Cortés & Enrique Romero-Mota
      - Caracterización de un suelo tropical por medio de ensayos in-situ
        - 211 Breno Padovezi Rocha & Heraldo Luiz Giacheti





- Melazas y vinaza de la caña de azúcar como sustrato para la producción de polihidroxialcanoatos (PHA) 220 Alejandro Acosta-Cárdenas, Wilman Alcaraz-Zapata & Mariana Cardona-Betancur
- Evaluación del uso del agua en PYMES de alimentos: Caso de estudio en una Planta de Beneficio Avícola en Colombia 226 Yelitza Angélica Zorrilla-Ortega, Juan Pablo Silva, Valentina Prado & Pablo César Manyoma
  - Pérdidas de nutrientes debido a la erosión hídrica con la lluvia simulada en el sur de Brasil
- Jeane Cruz Portela, Neroli Pedro Cogo, Jacques Carvalho Ribeiro Filho, Letícia Sequinatto, Rafael Oliveira Batista, Carolina Malala Martins Souza & Joaquim 236 Emanuel Fernandes Gondim
  - Efecto teratogénico sobre el desarrollo del tejido óseo en la cepa Wistar de Rattus norvegicus, inducida por la presencia de arsénico 242 Mireya Quiterio-Pérez, Juan Carlos Gaytán-Oyarzún, Alberto José Gordillo-Martínez & Francisco Prieto-García
    - Diseño v Cálculo de una Central Hibrida Solar-Hidráulica en Gran Canaria 250 Abian Beltrán, Herberth Gracia-León, Daniella Rodríguez-Urrego & Leonardo Rodríguez-Urrego
    - Electrocoaquiación de soluciones de índigo carmín empleando ánodos de magnesio y de aleación AZ31
- Dayana Donneys-Victoria, Cristian Camilo Ospina-Toro, Mónica Vanesa Zapata-Villegas, Nilson Marriaga-Cabrales, Fiderman Machuca-Martínez, Juan M. Peralta-258 Hérnandez & Carlos A. Martínez-Huitle
  - Integración SOA-MAS en ambientes inteligentes 268 Manuel Sánchez, Jose Aguilar & Ernesto Exposito
  - Un algoritmo de planificación en una clase de sistemas de eventos discretos 283
  - Guelvis Mata, Bladismir Ruiz, Claudia Camacho, Arnaldo Méndez, Sergio Muñoz & Hicher Zambrano
  - Beneficios agronómicos y ambientales de fuentes de fertilizantes nitrogenados en Ocimum basilicum L 294 Martha Constanza Daza-Torres, Greydy Selene Ladino-Tabarquino & Norberto Urrutia-Cobo
  - Evaluación del riesgo en procesos de tratamiento de agua para el desarrollo de un Plan de Seguridad del Agua PSA 304 Andrea Pérez-Vidal, Juan Carlos Escobar-Rivera & Patricia Torres-Lozada
    - Diseño de un motor de juegos serios emergentes basado en el algoritmo de optimización de colonia de hormigas 311 Jose Aguilar, Junior Altamiranda & Francisco Díaz
      - Herramienta de software para determinar constantes ópticas en celdas solares tipo película delgada
  - 321 Heiner Alexander Vargas-Perea, Robinson Rocha-González, Mónica Andrea Botero-Londoño, Alexander Sepúlveda-Sepúlveda & Clara Lilia Calderón-Triana Determination of Glacier retreat at Nevado del Ruiz, Santa Isabel and Tolima Volcanoes, Colombia through optical image and Din-SAR 329
    - Mario Fernando Monterroso-Tobar, Jhon Makario Londoño-Bonilla & Sergey Samsonov Demolition and construction waste characterization for potential reuse identification 338
      - Lina María Chica-Osorio & Juan Manuel Beltrán-Montoya
    - Relación entre el tamaño de partícula y el contenido de las fases cristalinas presentes en una escoria de aluminio 348
      - Adriana Gómez-Gómez, Luz Elena Vinasco, Nelson Batista de Lima & Jorge Aberto Soares Tenório



Nuestra carátula Imagen alusiva al artículo: Caracterización morfológica y nanomecánica de la fibra de Guadua Angustifolia kunth mediante SEM y AFM

### Autores:

Martin Eduardo Espitia-Nery, Dery Esmeralda Corredor-Pulido, Nelson Javier Rodríguez-Ramírez & Jeimy Natalia Calderón Bustos







## Soft Pre-stressed PET profiles as reinforcing fibers in structural elements made of concrete

Sergio Márquez-Domínguez<sup>*a*</sup>, Edgar Mejía-Sánchez<sup>*a*</sup>, Jesús Antonio Arenzano-Altaif<sup>*a*</sup>, Gerson Omar Martínez-Guevara<sup>*a*</sup> & Dante Tolentino<sup>*b*</sup>

<sup>a</sup> Facultad de Ingeniería, Universidad Veracruzana, C. Z. Mendoza, Veracruz State, México; semarquez@uv.mx, edmejia@uv.mx, jarenzano@uv.mx, germartinez@uv.mx

<sup>b</sup> Sección de Estudios de Posgrado e Investigación, ESIA Zacatenco, Instituto Politécnico Nacional, México, dtolentinolsro@gmail.com

Received: April 20th, 2018. Received in revised form: june 27th, 2018. Accepted: July 16, 2018

### Abstract

The inclusion of pre-stressed PET profiles as reinforcing fibers in structural elements is proposed. The PET-profiles are placed in a unidirectional and bidirectional fiber matrix with soft pre-tensioned condition that they could have advantages in structural members made of concrete in some precise applications, for instance, road safety barriers. A universal machine (WDW-200E) is used to test PET-profiles with different width, knots and even other conditions. The desired PET profile is chosen and the concrete mixture is designed under the ACI standard guidance. Pre-stressed PET-profiles are included in wood molds shaped in beam-type and subsequently flexural strength is estimated. Furthermore, experimental tests results are presented for PET-profiles as structural reinforcement of beams made of concrete under pure flexural. Finally, a probabilistic model is used to estimate the PET contribution in terms of exceedance of the rupture modulus.

Keywords: PET profiles; fiber matrix; beams-type; concrete; Pre-stress; PET fibers; probabilistic model

### Perfiles de PET ligeramente pretensados como fibras de refuerzo en elementos estructurales de concreto

### Resumen

Se propone la inclusión de perfiles de PET pretensados como fibras de refuerzo en elementos estructurales. Los perfiles de PET se colocan en una matriz de fibra unidireccional y bidireccional con una condición de pretensado suave que podría tener ventajas en elementos estructurales de concreto en algunas aplicaciones precisas, por ejemplo, barreras de contención para seguridad vial. Una máquina universal (WDW-200E) se usa para probar los perfiles de PET con diferentes anchos, nudos e incluso otras condiciones. Se elige el perfil de PET deseado y el concreto se diseña según la norma ACI. Los perfiles de PET pretensados se incluyen en moldes de madera con forma de vigas y, posteriormente, se estima la resistencia a la flexión. Los resultados de las pruebas experimentales de flexión son presentados. Finalmente, se usa un modelo probabilístico para estimar la contribución de PET en términos de excedencia del módulo de ruptura.

Palabras clave: Perfiles de PET; matriz de fibra; tipo viga; concreto; pre-tensados; fibras de PET; modelo probabilístico.

### 1. Introduction

### 1.1. State of the art

Environmental pollution is a serious issue that must be addressed as soon as possible. Polyethylene Terephthalate (PET or PETE) is considered a serious environmental problem that need to be studied in order to decrease its environment impact. According with INEGI [1], 44.646 million tons of urban solid waste were generated in Mexico by 2017; of which around 10% was classified as plastic waste. Carcaño [2], made an important prediction based on a study of supply-demand of PET products, establishing that the demand of PET products is going to be higher. One way to decrease this problem can be by implementing *"green building"*. These alternatives provide the opportunity to reuse

© The author; licensee Universidad Nacional de Colombia. @@@@@ Revista DYNA, 85(206), pp. 162-170, September, 2018, ISSN 0012-7353 DOI: https://doi.org/10.15446/dyna.v85n206.71805

How to cite: Márquez-Domínguez, S., Mejía-Sánchez, E., Arenzano-Altai, J.A., Martínez-Guevara, G.O. and Tolentino, D., Soft Pre-stressed PET profiles as reinforcing fibers in structural elements made of concrete. DYNA, 85(206), pp. 162-170, September, 2018.

toxic products and developed new building techniques, hence solid waste or polluting products can be integrated into useful structural elements that can even improve the building processes and also contribute to the mechanical properties of the structural elements. In order to understand the mechanical properties of concrete containing PET waste, several manuscripts have been conducted taken into account parameters such as elastic modulus [3-5], flexural tensile strengths [6-8], impact resistance [10], fresh and hardened properties of concrete [11] including abrasion resistance [9]. This research is presented as a structural context where PETprofiles were used as an alternative structural reinforcement, and also a probabilistic model is used to estimate the PET contribution in terms of exceedance of the rupture modulus.

### 2. Main scope

The main objective of this paper is to be the first national incursion on the subject of sustainable development through a prototype proposed to be implemented in the highway infrastructure. Here, the results are presented in order to assess the importance of using a PET-profiles matrix within concrete beam-type specimens where the flexural properties of concrete specimens reinforced by a soft pre-tensioned PET-profile matrix placed on in specially designed molds should be increased. PET-profiles settled as a fiber matrix with soft pre-tensioned condition could have advantages in structural members in some precise applications, as for instance, structural support for road safety barriers. Laboratory Tests are performed using a universal machine (WDW-200E) in order to estimate the tensile strength capacity of PET profiles with different width, number of "knots" and other conditions. The desired PET profile is chosen and the concrete mixture is designed under the ACI standard guidance [17]. The main stage is to estimate the flexural properties of reinforced concrete beams by including pre-stressed PET-profiles in order to develop a sustainable prototype that can be used in the highway infrastructure which are basically designed with a specified compressive strength of concrete ( $f_c=30MPa$ ).

### 2.1. The research process will cover the following phases

- 1. Analyze the mechanical and physical properties of the PET-profiles with different width, different number of "knots" and also many other conditions.
- 2. Perform Bending tests of concrete beams with loads in the thirds of their length.
- 3. Perform Bending tests of concrete beams including prestressed PET profiles in a unidirectional fiber matrix.
- 4. Perform bending tests of concrete beams with prestressed PET-profiles placed on a bidirectional fiber matrix in a mesh form.

In this paper a probabilistic assessment is used to estimate the PET contribution of the rupture modulus [12]. Here, the beamtype specimens are casted with concrete with a ( $f_c=30MPa$ )



Figure 1. Wooden molds within aluminum accessories and PET-profiles matrix: 5 layers with 11 threads every layer. Source: The authors.

complying with NMX-C-159-ONNCCE-2004 [13] and NMX-C-160-ONNCCE. 2004, MEXICO: ONNCCE [14]. These standard codes are used for the preparation of test specimens. In order to estimate the flexural strength capacity of beam-type specimens, it is worth to mention that, the molds are built with a cross section of  $0.15 \times 0.15$  m and length equal to 0.60 m, made of wood. The wooden molds will include different aluminum accessories necessary to hold the PET-fibers, then it is possible make a soft pre-stressing, see Fig. 1.

### 3. PET-profiles: Tensile strength capacity

The PET-profiles and/or PET-threads were tested one by one in blocks with similar geometric properties in order to estimate an average of the tensile strength capacity and deformation of each block. The PET-profiles were cut and prepared from recycled PET-bottles coming from commercial sodas. In Table 1 to 6, valuable information is given obtained for PET-profile with different width (Table 1), number of "knots" (Tables 2) and also other properties were analyzed such as for instance the temperature effect. It is worth to mention that the tensile strength was estimated in a Universal Testing Machine (WDW-200E),

The necessity of workability, when the PET-profiles are implemented in the wooden molds is very important. For this reason and according with the tests results given in Table 1, it was decided to use PET-profiles with  $3.5 \times 10^{-3}$  m of width. On the other hand, knotted PET-profiles have the "anchorage"

| Ta | ble | 1. |
|----|-----|----|
|    |     |    |

Tensile strength capacity of PET-profiles with different widths and a length equal to 0.25 m and Thickness  $4.5\ x10^4\ m$ 

| No. of<br>specimens | Width<br>(m)          | Deformation<br>(m) | Tensile strength<br>capacity (N) |
|---------------------|-----------------------|--------------------|----------------------------------|
| 10                  | 3.5 x10 <sup>-3</sup> | 0.06690            | 180.11                           |
| 10                  | 5.0 x10 <sup>-3</sup> | 0.05213            | 240.15                           |
| 10                  | 7.0 x10 <sup>-3</sup> | 0.03712            | 344.23                           |
| 10                  | 1.0 x10 <sup>-2</sup> | 0.04175            | 392.20                           |

Source: The authors.

T 11 (

| Table 2.   |
|--|
| Tensile strength capacity from knotted PET-profiles with a width 3.5 x10 |
| m length equal to 0.25 m and Thickness 4.5 $\times 10^{-4}$ m            |

| No. of<br>specimens | No. of Knots | Deformation<br>(m) | Tensile strength<br>canacity (N) |
|---------------------|--------------|--------------------|----------------------------------|
| 10                  | 1            | 0.03893            | 160.10                           |
| 10                  | 2            | 0.03579            | 140.09                           |
| 10                  | 3            | 0.10731            | 160.09                           |
| 10                  | 5            | 0.11929            | 152.06                           |
| 10                  | 7            | 0.08620            | 124.10                           |
| 10                  | 10           | 0 17620            | 136.06                           |

Source: The authors

Table 3.

Tensile strength capacity from PET-profiles baked at 50 °C with a width  $3.5 \times 10^{-3}$  m, length equal to 0.25 m and Thickness  $4.5 \times 10^{-4}$  m

| No. of<br>specimens | Baking time<br>(s) | Deformation<br>(m) | Tensile strength<br>capacity (N) |
|---------------------|--------------------|--------------------|----------------------------------|
| 5                   | 900                | 0.04108            | 248.19                           |
| 5                   | 1,800              | 0.04025            | 280.17                           |
| 5                   | 2,700              | 0.04198            | 224.16                           |
| 5                   | 3,600              | 0,04720            | 248.19                           |

Source: The authors

#### Table 4.

Tensile strength capacity from PET-profiles baked at 100 °C with a width  $3.5 \times 10^{-3}$  m, length equal to 0.25 m and Thickness  $4.5 \times 10^{-4}$  m

| 5 | No. of<br>specimens | Baking time<br>(s) | Deformation<br>(m) | Tensile strength<br>capacity (N) |
|---|---------------------|--------------------|--------------------|----------------------------------|
|   | 5                   | 900                | 0.09516            | 272.13                           |
|   | 5                   | 1,800              | 0.11167            | 264.18                           |
|   | 5                   | 2,700              | 0.06349            | 216.11                           |
|   | 5                   | 3,600              | 0.05337            | 176.11                           |

Source: The authors

function working together with concrete; these knots will be like the corrugations in the steel rods. In this study, Knotted PET-profiles are the most viable option granting the anchorage between PET-Profiles and concrete, see Fig. 1.

Knotted PET-profiles provide similar tensile strength capacity than not knotted PET-profiles, see Table 2 where a total of 60 test specimens were tested in blocks each one with 10 specimens with similar knotted conditions in order to estimate an average of the tensile strength capacity and deformation of each block. Even, in this research work, the effect of temperature on the PET is reviewed since the particles of the material could be crystallized providing a change in their mechanical properties. The Tensile strength estimated from PET- profiles baked at different temperatures are presented in Tables 3 to 5 where 5 tests are reported for each time step and temperature, these number of tests were considered enough evidence to observe the behavior of the effect of temperature on PET-profiles.

Table 5.

Tensile strength capacity from PET-profiles baked at 150 °C with a width  $3.5 \times 10^{-3}$  m, length equal to 0.25 m and Thickness  $4.5 \times 10^{-4}$  m

| No. of<br>specimens | Baking time<br>(s) | Deformation<br>(m) | Tensile strength<br>capacity (N) |
|---------------------|--------------------|--------------------|----------------------------------|
| 5                   | 900                | 0.10644            | 200.12                           |
| 5                   | 1,800              | 0.08161            | 176.09                           |
| 5                   | 2,700              | 0.09000            | 160.10                           |
| 5                   | 3,600              | 0.06491            | 184.13                           |

Source: The authors

| l'able o.  |  |
|--|--|
| Tensile strength capacity of extruded Plastic-profiles made off with |  |
| commercial plastic bags: length 0.15 m                               |  |

| No. of<br>specimens | Diameter<br>(m)        | Deformation<br>(m) | Tensile strength<br>capacity (N) |
|---------------------|------------------------|--------------------|----------------------------------|
| 7                   | 3.50 x10 <sup>-3</sup> | 0.21484            | 125.76                           |
| 7                   | 4.85 x10 <sup>-3</sup> | 0.24998            | 240.15                           |
| 7                   | 5.75 x10 <sup>-3</sup> | 0.24976            | 314.21                           |

Source: The authors



Figure 2. Extruded Plastic-Profiles. Source: The authors.

The Plastic-profiles can be made off with recycled plastic material coming from commercial plastic bags, See Fig. 2 where extruded Plastic-profiles are shown. In Table 6, is clear that the deformation of the Plastic-profiles is greater than that experienced by the PET-profiles given in Table 1. In fact, the tests carried out under controlled laboratory test conditions proved that "Plastic-profiles", with circular cross-section, resist a certain tensile strength capacity without reaching their rupture, it means that the Plastic-profiles are working in the plastic zone area.

A considerable number of Tests were carried out with different diameters of extruded Plastic-profiles, see Table 6 where it is shown that the Plastic-profile of  $5.75 \times 10^{-3}$  m in diameter has the highest tensile strength capacity.

It is worth to mention that for 1 kg of plastic material; the following material is required:

- 0.772kg of recycled Linear Low-Density Polyethylene (LLDPE).
- 0.154kg of recycled High Density Polyethylene (HDPE).
- 0.074kg. of recycled Low Density Polyethylene (LDPE)

The last three materials can be recycled from commercial plastic bags.

### 4. Concrete Beam-type specimens: Flexural strength capacity

The concrete was designed with a specified compressive strength of (f'c = 30MPa). The compressive strength of concrete is measured to ensure that the concrete satisfy the quality control. To measure the compressive strength of the concrete, cylindrical-test specimens of 0.15 x 0.30 m are prepared and stored until the concrete hardens. The whole testing procedure was carried out in laboratory test conditions following the standard codes, see [13-15].



Figure 3. Beam-type specimen with PET-profiles settled in a bidirectional fiber matrix in a mesh form. Source: The authors



Figure 4. Concrete Flexural Resistance using a simple concrete beam with load in the middle third of the clearing. NMX-C-191-ONNCCE [15]. Source: The authors

Once the concrete mixture is designed and tested. The concrete is casted in molds made off wood with cross-section  $0.15 \times 0.15 \times 0.50$  m. Every PET-thread had knots every 0.02 m to provide traction and an additional pre-tension was induced (approximately - 1 kg per thread). A cast beam-type specimen with the PET-profile matrix is shown in Fig. 3.

Now, it is possible to perform bending tests in order to estimate the flexural strength of concrete beams-type specimens with loads in the thirds of their length with and without PET-profiles embedded following a unidirectional fiber matrix or a bidirectional fiber matrix in a mesh form.

According with NMX-C-191-ONNCCE [15], the modulus of rupture is a material property obtained to determine the flexural strength of the concrete by the bending test of a beam. There are two types of failure in terms of the rupture modulus, when the fracture is presented in the middle third of the clearing, see Fig. 4 and when the rupture is not presented within the middle third.

Therefore, on average, two beam-type specimens were casted per every test stage so that in total around 18 tests beam-type specimens were done obtaining the following results. In Table 7, the bending test results for beam-type specimens made of simple concrete are shown with loads in the thirds of their length.

Table 7.

| ** * | Main data obtained fro | m Beam-type specimens | made of simple concrete |
|------|------------------------|-----------------------|-------------------------|
|------|------------------------|-----------------------|-------------------------|

| Day                          | 3                     | 7         | 28       |
|------------------------------|-----------------------|-----------|----------|
| Maximum load (KN)            | 24.255                | 28.838    | 23.894   |
| Deformation (m)              | 2.4 x10 <sup>-3</sup> | 1.6 x10⁻³ | 7.8 x10⁻ |
|                              |                       |           | 3        |
| Modulus of rupture (MPa)     | 3.66                  | 4.35      | 3.60     |
| Rotation ( $\theta$ -grades) | 8°                    | 5°        | 14°      |
| Source: The authors          |                       |           |          |

| Table  | 8.     |            |        |             |           |      |      |             |    |
|--------|--------|------------|--------|-------------|-----------|------|------|-------------|----|
| Main   | data   | obtained   | from   | Beam-type   | specimens | made | with | PET-profile | 25 |
| nlaced | d in a | unidirecti | onal f | iber matrix |           |      |      |             |    |

| Day                          | 3                     | 7                     | 28            |  |  |
|------------------------------|-----------------------|-----------------------|---------------|--|--|
| Maximum load (KN)            | 37.093                | 36.673                | 36.743        |  |  |
| Deformation (m)              | 6.4 x10 <sup>-3</sup> | 5.4 x10 <sup>-3</sup> | 5.8 x10⁻<br>₃ |  |  |
| Modulus of rupture (MPa)     | 5.60                  | 5.53                  | 5.54          |  |  |
| Rotation ( $\theta$ -grades) | 21°                   | 17°                   | 19°           |  |  |
| Source: The authors          |                       |                       |               |  |  |

Source: The authors

Table 9.

Main data obtained from Beam-type specimens made with PET-profiles placed in a bidirectional fiber matrix (45°, Fig. 3).

| Day                          | 3                     | 7         | 28       |
|------------------------------|-----------------------|-----------|----------|
| Maximum load (KN)            | 29.858                | 28.857    | 25.836   |
| Deformation (m)              | 7.3 x10 <sup>-3</sup> | 7.5 x10⁻³ | 6.5 x10⁻ |
|                              |                       |           | 3        |
| Modulus of rupture (MPa)     | 4.50                  | 4.35      | 3.90     |
| Rotation ( $\theta$ -grades) | 23°                   | 24°       | 21°      |
| Source: The authors          |                       |           |          |

In Table 8 and 9, the bending tests results coming from beam-type specimen whit pre-stressed PET profiles in a unidirectional and bidirectional fiber matrix are given, respectively.

The average of the maximum load capacity and deformation are obtained from beam-type specimens casted at different ages; see Tables 7 to 9 where Fluctuated load capacity values are observed. The PET-profiles in a unidirectional and bidirectional matrix arrangement have influence in the flexural strength capacity of the beams-type specimens. In Tables 7 to 9, The deflection has also an considerable importance in the load capacity and modulus of rupture where a soft increment in the value are observed in beam-type specimens with PET-profiles settled in a uni and bi-directional matrix. It is because the beam-type specimens with PET-profiles can support more deflection. The influence of the PET-profiles is higher in the test specimens with a unidirectional arrangement than in a bidirectional matrix where the PET-profiles settled with a 45° angle could affect the behavior of the unidirectional PET-Profile arrangement which could work once the concrete have failed. In Tables 7 to 9, the rotation is estimated using the data of maximum load and deformation. It is easy to see that the PET-profiles provide a better rotation degree to the beam where, the beamtype specimens made with PET-profiles placed in a bidirectional fiber matrix placed to 45° have higher rotation and flexibility with similar flexural strength those beam-type specimens with a unidirectional fiber matrix.

In Table 2 is shown that a thread with 10 knots can resist a load of 135.97 N. But according to data in Tables 7 to 9, it is not easy to see the contribution of tensile and flexural strength. For this reason, it is necessary to analyze the Figs. 5-7.

In Fig. 5, the beam specimen reaches the maximum load and after that a fragile failure is presented. That is not the case for beam specimens with unidirectional and bidirectional PET fiber matrix where, the PET profiles provides a 62-63% average resistance after the failure of concrete, see Fig. 6 and 7. In Fig. 7, PET-profiles placed in a bidirectional matrix with 45° provide a 6.46% more compared to profiles settled in a



Figure 5. Load-Deflection for a simple concrete beam loaded in the middle third of the clearing. NMX-C-191-ONNCCE [15]. Source: The authors

unidirectional way. Therefore, PET-profiles settled in a bidirectional matrix with 45° provides around 69.31% more than a simple concrete beam after the fragile failure, it should be mentioned that these test specimens with PET-profiles shown a remarkable strength increase upwards compared to the profiles placed in a unidirectional way; showing a "constant" or linear contribution.



Figure 6. Load-Deflection for a beam-type made off concrete with unidirectional fiber matrix loaded in the middle third of the clearing. NMX-C-191-ONNCCE [15]. Source: The authors



Figure 7. Load-Deflection for a beam-type made off concrete with bidirectional fiber matrix loaded in the middle third of the clearing. NMX-C-191-ONNCCE [15]. Source: The authors

Fig. 5 shows a tests specimen with fragile failure, it is because the PET profiles are not included. In Fig. 6 and 7, the contribution of the PET profiles are working once the concrete fail. Therefore, the curves in the figures show that the tests specimen is holding strength and lead to a ductile failure.

Fig. 8 shows that PET-profiles have the characteristic to keep the concrete fragments confined due to the action or anchoring provided by knotted PET profiles. Therefore, the PET-profiles inclusion in the concrete can be useful in structural support for road safety barrier where the car impact can spread small concrete fragments and the PET-profiles or PET-threads could keep the concrete fragments confined. Future work can be planned where impact tests and energy dissipation can be carried out, since the PET profiles has the ability to confine the concrete particles where the main objective of this project is to save the life of the road users and protect the environment.



Figure 8. Fragments confined in a beam specimen due to the anchoring provided by knotted PET profiles placed in a bidirectional fiber matrix. Source: The authors

#### 5. Probabilistic estimation of PET-profiles contribution

In this section, a probabilistic approach is proposed to evaluate PET-Contribution in terms of capacity and failure. In Table 10, the stochastic variables are enumerated. It is worth to mention that PET contribution affects more the vicinity of flexural failure stage when these profiles are delaying the Rupture modulus (RM) while the flexural beam upper compression block is increasing (or decreasing) to balance the flexural capacity. Therefore, the rupture modulus test considers an early state during beam behavior before tension-cracking condition where it is always expected a sudden and brittle beam failure.

The values shown in Table 10 are based on preliminary test studies which have been carry out in [12] where a modulus of rupture of 3.54MPa was obtained for a beam-type specimen made of 20MPa and beams including pre-stressed PET profiles in a unidirectional fiber matrix a modulus of rupture of 3.788MPa was estimated, which clearly is compatible with the results presented in Tables 7 to 9 where Beam-type specimens with a compressive strength of 30MPa which have been tested.

Eq. (1) is used to estimate the tension stress in the bottom fiber where rupture is taking place:

Table 10.

Stochastic variables and models for Probabilistic simulation of PETcontribution before flexure rupture

| No.   | Variable  | Values                          | Description            |  |
|---|---|---------------------------------|------------------------|--|
| 1   | $h \sim LN(\mu_h, \sigma_h)$                      | $\mu_h = 0.15$ ,                | Beam height (m)        |  |
|   |   | $\sigma_h = 0.2  (\%)$          |                        |  |
| 2   | $b \sim LN(\mu_b, \sigma_b)$                      | $\mu_b = 0.15$ ,                | Beam base (m)          |  |
|   |   | $\sigma_b = 0.2  (\%)$          |                        |  |
| 3   | $P \sim LN(\mu_P, \sigma_P)$                      | $\mu_P, \sigma_P,$ according    | Rupture test load      |  |
|   |   | analysis                        | (N)                    |  |
| 4   | $f_t \sim LN(\mu_{ft}, \sigma_{ft})$              | $\mu_{ft} = 3.54$ ,             | RM (MPa)               |  |
|   |   | $\sigma_{ft} = 0.4  (\%)$       |                        |  |
| 5   | $\varepsilon_{cu} \sim LN(\mu_{cu}, \sigma_{cu})$ | $\mu_{cu} = 0.000038$           | Ultimate               |  |
|   |   | $\sigma_{cu} = 0.000002$        | compressive            |  |
|   |   |                                 | deformation            |  |
| 6   | $l_w \sim LN(\mu_{lw}, \sigma_{lw})$              | $\mu_{lw} = 0.60$               | Beam total length      |  |
|   |   | $\sigma_{lw} = 0.4  (\%)$       | (m)                    |  |
| 7   | $l_P \sim LN(\mu_{lP}, \sigma_{lP})$              | $\mu_{lP} = 0.50$ ,             | Beam test length       |  |
|   |   | $\sigma_{lP} = 0.4  (\%)$       | (m)                    |  |
| 8   | $w_{tot} \sim LN(\mu_{wt}, \sigma_w)$             | $\mu_{wt} = 255.06$             | Total beam weight      |  |
|   |   | $\sigma_{wt} = 10$              | (N)                    |  |
| 9   | $f'_c \sim LN(\mu_{fc}, \sigma_{fc})$             | $\mu_{fc} = 20$                 | Design compressive     |  |
|   |   | $\sigma_h = 1.5$                | of concrete (MPa)      |  |
| 10  | $n_{sim} \sim D$                                  | According analysis              | Number of              |  |
|   |   |                                 | simulations            |  |
| 11  | $n_{pp} \sim D$                                   | Matrix of 3 layers, 6           | Number of PET-         |  |
|   |   | profiles within layer.          | profiles. Total 18     |  |
| 10  |   | 0.000.005                       | profiles.              |  |
| 12  | $p_t \sim N(\mu_{pt}, \sigma_{pt})$               | $\mu_{pt} = 0.000635$           | Thickness of PET-      |  |
|   |   | $\sigma_{pt} = 0.0001$          | profile (m)            |  |
| 13  | $p_b \sim N(\mu_{pb}, \sigma_{pb})$               | $\mu_{pb} = 0.003$ ,            | Cross-section base     |  |
|   |   | $\sigma_{pb} = 0.0005$          | of PET-profile (m)     |  |
| 14  | $p_{yi} \sim N(\mu_{yi}, \sigma_{yi})$            | $\mu_{yi}$                      | i-th distance of layer |  |
|   |   | = (0.02, 0.04, 0.06)            | from the bottom of     |  |
|   |   | $\sigma_{yi} = (0.1, 0.1, 0.1)$ | the beam (m).          |  |
|   |   | (%)                             |                        |  |
| 15  | $p_E \sim N(\mu_{pE}, \sigma_{pE})$               | $\mu_{pE} = 7138.0135$          | Commercial             |  |
|   |   | $\sigma_{nE} = 120$             | Young's modulus of     |  |
|   |   | P 2                             | PET-profile (MPa)      |  |
| Note: D: Deterministic value, N: Normal distribution and LN: Log-normal |   |                                 |                        |  |

$$f_{c} = f_{Hm} \left[ f_{H}^{-1} \left[ \frac{\left( \frac{w_{tot} l_{w}}{16} + \frac{P l_{p}}{6} \right) (d_{f})}{\left( \frac{b h^{3}}{12} \right)}, f'_{c'} E_{c} \left( \frac{w_{tot}}{h b l_{w}}, f'_{c'}, f_{t}, \varepsilon_{cu} \right) \right] \right]$$
(1)

Where  $f_H^{-1}(\cdot)$  and  $f_{Hm}(\cdot)$  are the inverse Hognestad's stress-deformation model for nonconfined concrete and simple numerical modification of Hognestad's stress-deformation model for nullifying tension stresses in the lower part of the beam, see reference [16]. The first term in  $f_H^{-1}(\cdot)$  is the flexural normal stress  $\sigma$  and the last is a Young's modulus that is calculated using a former ACI contribution [17]. The total weight of the specimen is considered as uncertainty. The variable  $d_f$  is the distance to the section fiber in which one is interested on. Thinking in the top or bottom layers,  $d_f = h/2$ .

With the inclusion of PET-profile, the bottom stress  $(\sigma_h)$ and top stress ( $\sigma_t$ ) may change with the hand of the stress diagram of a supposed plain remaining face. In Fig. 9, it is shown the case 9-a where PET-profiles are not included. Also, the condition of PET embedded is considered in 9-b and 9-c. In the Fig. 9-b, it is shown the case in which any reinforcing fibers (general case) are contributing to the tension wedge force and as a result, the compression force should increase in a manner of an area increasing. In the case of Fig. 9-c, the condition of a reinforcing soft fiber is prevailing. In the former case, the fibers are reducing concrete area at tension wedge and hence, the tension force should increase (with an increasing of tension wedge area). Previous cases in Fig. 9-b, 9-c, can be the cases of PETprofiles. The diverse behavior depends directly on the Young's modulus of PET-profiles as theory is describing but also any initial pre-tensioning of PET-fibers (as is the case) according the PET variety and conditions.

Assuming the behavior in Fig. 9-b, the PET contribution may be positive for increasing RM or generating cases where  $\sigma_b$  is less than  $\sigma_t$ . The experimental data of the beams in this work, confirm this belief. In order to include in the eq. (1) with the variation of  $d_f$  and using:



Figure 9. Effects of PET-profiles. (a) Stress diagram without PET-profiles. (b) Stress diagram with PET-profile and increasing of compression wedge area. (c) Stress diagram with PET-profile and decreasing of compression wedge area. -Source: [12]

Note: D: Deterministic value, N: Normal distribution and LN: Log-normal distribution.

Source: Taken from [12]

Table 11

$$c = \frac{2(F_C \pm \sum_{i=1}^{n_f} f_i)}{b\sigma_h} \tag{2}$$

where c is the compression wedge depth,  $F_c$  is the Compression resulting force,  $f_i$  is the fiber force, b is the cross-sectional base and  $\sigma_b$  is the bottom tension stress. The signs  $\pm$  are referring to softfibers (+, sign) and acting-fibers (-, sign), respectively. Using the eq. (2), it is possible to calculate (1) and estimate the modification of the stress profile. When the eq. (1) is modified by (2), it is possible to simulate by Monte Carlo technique and then find the positive or negative contribution of the PET-profile.

The limit state equation can be described by:

$$g(\tilde{x}) = f_{tb} - f_{cb} \tag{3}$$

where  $\tilde{x}$  is the vector of stochastic and deterministic parameter shown in Table 10 and  $f_{tb}$  is the stochastic variable representing the maximum tension stress at the bottom line of the cross section and  $f_{cb}$  is the bottom stress calculated with  $f_c$  using the eq. (3) as  $d_f$ .

### 6. Application case

In Table 11, the results are shown which they basically address the tests made in beam-type specimens with simple concrete ( $f_c=20$  MPa), where two different molds were used: a conventional 0.15 x 0.15 x 0.45 m and other with 18 holes to introduce the PET-profiles which have been carry out in [12].

From Table 11, it is possible to see an increase of reliability ( $\beta$ ) for specific values of P, coming from expected forces for particular compressive strength of concrete in specific tested beams. And also low reliability  $\beta$ -values are referring to the tension cracking condition from the fact that this condition is not preventable. However, it is more important to be concentrated in the difference between beam's reliability indexes ( $\beta$ ) with and without PET-profiles. The differences are mainly what this work is about.

In this paper, the tests are made in beam-type specimens with simple concrete ( $f_c$ =30MPa). This is done mainly for structural applications mainly for a Highway Safety barrier prototype complying with the standard code "NMX-C-159-ONNCCE-2004" [13], where two different molds were used: a conventional 0.15 x 0.15 x 0.50 m and other with 55 holes to introduce the PET-profiles in a matrix with 5 layers with 11 threads every layer. Every PET-thread had knots every 0.02 m to provide traction and an additional pre-tensioning was induced (approximately 1 kg per thread). Beam-test specimens without PET-profiles has a Rupture modulus in average equal to 3.60MPa and Beam-type specimens made with PET-profiles placed in a unidirectional fiber matrix has an estimated Rupture Modulus around 5.54MPa (see Table 8) and 3.90MPa with PET-profiles placed in a bidirectional fiber matrix (45°, Table 9).

National Road Accident Statistics is widely addressed in [18]. In fact, injuries caused by traffic accidents are still among the ten leading causes of death in Mexico, in 2014, 15,886 deaths were registered. Therefore, a rate of 13.3 deaths per 100 thousand inhabitants is estimated. According with above, the possibility of a car accident is high and should be taken into account carefully.

Reliability results for beam specimen made of 20MPa

| P<br>Rupture test<br>load<br>parameters<br>(KN) | RM-<br>Exceedance<br>probability<br>without<br>PET | RM- RM-<br>Exceedance<br>probability<br>without<br>PET with PET |        | β with<br>PET-<br>profiles |
|---|--|---|--------|----------------------------|
| $\mu_P = 25.0,$                                 | 0.078  | 0.072   | 1.4186 | 1.4610                     |
| $\sigma_P = 0.5$                                |  |   |        |                            |
| $\mu_P = 25.0$ ,                                | 0.164  | 0.155   | 0.9781 | 1.015                      |
| $\sigma_P = 1.0$                                |  |   |        |                            |
| $\mu_P = 27.0$ ,                                | 0.072  | 0.069   | 0.588  | 0.5129                     |
| $\sigma_P = 0.5$                                |  |   |        |                            |
| $\mu_P = 27.0$ ,                                | 0.0642   | 0.0617  | 0.3638 | 0.2976                     |
| $\sigma_P = 1.0$                                |  |   |        |                            |

Source: Taken from [12]

### 7. Highway safety barrier prototype

Car accidents are presented due to various conditions and it is easy that the vehicles lose their trajectory causing accidents that endanger the lives of passengers and other road users. For this reason, the development of new technologies in this area is important. In consequence, road safety barriers are installed and designed in accordance with strict technical criteria, in order to achieve maximum efficiency avoiding major damage to road users. Highways have mostly road safety barriers dividing the main lanes. Due to the above, PET profiles can be added to the safety barriers potentializing considerably the PET recycling.

Safety barriers with PET-profiles matrix is an initial prototype as a proposal that need to be studied in detail, see Fig. 10 and 11. The initial model has PET-profiles placed in a bidirectional matrix where PET-profiles are settled with 0.15 m between each one following the vertical direction of the cross section, this arrangement is an initial purpose thinking in easy enabled and placed inside the mold of the safety barrier. For future investigations, it is recommended to conduct impact studies to determine the effectiveness of the proposed model and determine the release of energy as presented in the prototype. Therefore, the PET-profiles inclusion in the concrete can be useful in structural support for road safety barrier where the car impact can spread small concrete fragments and the PET-profiles or PET-threads could keep the concrete fragments confined.



Figure 10. Pure bending device built according to 0.075 m [-C-191-ONNCCE [15] standard. Source: The authors



Figure 11. Pure bending device built according to the NMX-C-191-ONNCCE [15] standard. Source: The authors

### 8. Conclusions

Green building is the opportunity to reuse toxic products and developed new building techniques in such a way that polluting products can be integrated into useful building elements that can even improve the building processes and also contribute to the mechanical properties of the structural elements. Therefore, this paper is an initial addressing PETprofiles reinforcing for failure structural states. In fact, it is presented experimental tests of a PET-profile matrix as tension reinforcement of beams made of concrete under pure flexural test. It was shown that PET-profiles used in unidirectional and bidirectional fiber matrix with soft pretensioned condition could have advantages in structural members in some precise applications, as for instance members impose to impact such as road safety barriers implemented in the highway infrastructure where PETprofiles inclusion in the concrete can be useful in structural support when a car impact can spread small concrete fragments and the PET-profiles or PET-threads could keep the concrete fragments confined and also the PET-fibers can be helpful in the vicinity of cracking failure condition, having three main aspects: a subtle increasing rupture modulus, crack mitigating in the failure plane and providing an additional plastic PET-capacity after failure. From the structural reliability perspective, PET-threads have influence, rising the reliability levels for expected forces for a particular compressive strength of structural members. It is worth to say that the stochastic model match properly with the experimental test.

### Acknowledgements

The authors acknowledge the support of Program for Professional Teacher Development, for the Higher Type (PRODEP) through the project called SA/103.5/16/10438 /PTC-835. The authors want to make a special thanks to the students Sergio Jesús López-Castañeda, José Melesio Sánchez-Morales, Abelardo Molohua-Texoco due to the valuable help and effort by carrying out the laboratory tests

### References

- National Institute of Statistic and Geography (INEGI). Statistical and Geographical Yearbook of the United Mexican States, National Institute of Statistic and Geography. 2017, Mexico, 1066 P.
- [2] Reyes-Carcaño, J.R., Estudio de factibilidad para la instalación de una planta recicladora de envases de PET. BSc. Thesis, Unidad Profesional Interdisciplinaria de Ingeniería y Ciencias Sociales y Administrativas (UPUESA), Instituto Politécnico Nacional, México, 2009.
- [3] Hannawi, K., Kamali-Bernard, S. and Prince, W., Physical and mechanical properties of mortars containing PET and PC waste aggregates. Waste Management, 30, pp. 2312-2320, 2010. DOI:10.1016/j.wasman.2010.03.028
- [4] Mohammed, A.A., Flexural behavior and analysis of reinforced concrete beams made of recycled PET waste concrete. Construction and Buildings Materials, 155, pp. 593-604, 2017. DOI: 10.1016/j.conbuildmat.2017.08.096
- [5] Mohammed, A.A., Modeling the mechanical properties of concrete containing PET waste aggregate. Construction and Buildings Materials, 150, pp. 595-605, 2017. DOI: 10.1016/j.conbuildmat.2017.05.154
- [6] Bhogayata, A.C. and Arora, N.K., Fresh and strength properties of concrete reinforced with metalized plastic waste fibers. Construction and Buildings Materials, 146, pp. 455-463, 2017 DOI: 10.1016/j.conbuildmat.2017.04.095
- [7] Rebeiz, K.S., Precast use of polymer concrete using unsaturated polyester resin based on recycled PET waste. Construction and Buildings Materials, 10(3), pp. 215-220, 1996.
- [8] Rinu-Isah, R.J. and Shruthi M.V., Utilization of waste PET bottle fibers in reinforced concrete. International Journal of Pure and Applied Mathematics, 116(13), pp. 579-584, 2017. ISSN: 1311-8080 (printed version); ISSN: 1314-3395 (on-line version)
- [9] Saikia, N. and De Brito, J., Mechanical properties and abrasion behavior of concrete containing shredded bottle waste as a partial substitution of natural aggregate, Construction and Buildings Materials, 52, pp. 236-244, 2014. DOI: 10.1016/j.conbuildmat.2013.11.049
- [10] Saxena, R., Siddique, S. Gupta, T., Sharma, R.K. and Chaudhary, S., Impact resistance and energy absorption capacity of concrete containing plastic waste, Construction and Buildings Materials, 176, pp. 415-421,2018. DOI: 10.1016/j.conbuildmat.2018.05.019
- [11] Pacheco-Torgal, F., Ding, Y. and Jalali, S., Properties and durability of concrete containing polymeric wastes (tire rubber and polyethylene terephthalate bottles): an overview, Construction and Buildings Materials, 30, pp.714-724, 2012. DOI: 10.1016/j.conbuildmat.2011.11.047
- [12] Márquez-Domínguez, S. et al., Residual PET profiles as tension reinforcing fibers in beams. Proceedings of 6th Structural Engineers World Congress (SEWC). Cancún, Mexico. November 14-17, 2017.
- [13] National Agency for Standardization and Certification of Construction and Building. Mexican Standard- NMX-C-159-ONNCCE. 2004, MEXICO: ONNCCE.
- [14] National Agency for Standardization and Certification of Construction and Building. Mexican Standard- NMX-C-160-ONNCCE. 2004, MEXICO: ONNCCE.
- [15] National Agency for Standardization and Certification of Construction and Building. Mexican Standard-NMX-C-191-ONNCCE. 2004. Concrete flexural resistance using a simple beam with load in the clear thirds. MEXICO: ONNCCE.
- [16] Hognestad, E., A Study of combined bending and axial load in reinforced concrete members. University of Illinois Engineering Experimental Station, Serie number 399, November 1951, 128 P.
- [17] ACI Committee 318, Building Code Requirements for Reinforced Concrete, American Concrete Institute, Detroit, 1971.
- [18] Report on the situation of road safety, Mexico 2015. Secretariat of Health/STCONAPRA. Mexico, [online]. 2016. ISBN: 978-607-460-534-1. Available at: http://conapra.salud.gob.mx/Interior/ Documentos/Informe2015.pdf

**S. Márquez-Dominguez,** received the BSc. Eng in Civil Engineering in 2004 by the Universidad Veracruzana, the MSc. degree in Engineering in 2006 from Universidad Nacional Autónoma de Mexico (UNAM), both in Mexico and the PhD degree in Civil Engineering in 2013 from Aalborg

University in Denmark. From 2013 to 2014, he worked as a full professor in civil engineering in Universidad de Guanajuato, Mexico and since 2014, he is a full professor in the Civil Engineering Department, Facultad de Ingeniería, Universidad Veracruzana; Mexico. His research interests include: structural reliability, materials and sustainable construction or green building as an opportunity to reuse toxic products and developed new building techniques.

ORCID: 0000-0002-4864-3238

**E. Mejía-Sánchez,** received the BSc. Eng in Electromechanical Engineering in 2001 by the Instituto Tecnológico de Apizaco, the MSc. degree in Mechanical Engineering in 2004 from Centro Nacional de Investigación y Desarrollo Tecnológico (CENIDET) and the PhD degree in Engineering and Applied Sciences in 2010 from Universidad Autónoma del Estado de Morelos, all in Mexico. From 2001 to 2009, he worked as a full professor in Mechanical Engineering in Universidad Tecnológica Emiliano Zapata (UTEZ), Morelos, Mexico and since 2009, he is a full professor in the Mechanical Engineering Department, Facultad de Ingeniería, Universidad Veracruzana. His research interests include: materials and sustainable construction.

ORCID: 0000-0002-9806-6141

J.A. Arenzano-Altaif, Completed his BSc. degree in Industrial Engineering in 1998 and a MSc. degree in Industrial Engineering in 2004, both at Instituto Tecnologico de Orizaba, also completed a Doctorate in Engineering in 2017 at Universidad Veracruzana. He is currently full time professor at the Faculty of Engineering, campus Cd. Mendoza, of Universidad Veracruzana. His research works include advanced materials in the area of polymers. ORCID: 0000-0001-5201-1527

**G.O. Martinez-Guevara**, received the BSc. Eng in Civil Engineering in 2004 by the Technological Institute of Tehuacan, the MSc. of Applied Engineering in 2015 from Universidad Veracruzana, both in Mexico. And since 2011, he is a full professor in Facultad de Ingeniería, Universidad Veracruzana in the Engineering Department and responsible for the laboratory of soil and materials mechanics. His research interests include: technology in materials, as an opportunity to implement the use of materials in new technologies.

ORCID: 0000-0002-8040-9097

**D.** Tolentino, completed his BSc. in Civil Engineering at Instituto Politécnico Nacional in 2007, a MSc. in Engineering in 2009 and a PhD in Engineering in 2013 all of them at Universidad Nacional Autónoma de Mexico. He is currently professor at the Seccion de Estudios de Posgrado e Investigación of the Escuela Superior de Ingeniería y Arquitectura Unidad Zacatenco at the Instituto Politécnico Nacional. He is an expert in structural reliability and optimization. ORCID: 0000-0003-3930-3562



UNIVERSIDAD NACIONAL DE COLOMBIA SEDE MEDELLÍN FACULTAD DE MINAS

Área Curricular de Ingeniería Civil

Oferta de Posgrados

Especialización en Vías y Transportes Especialización en Estructuras Maestría en Ingeniería - Infraestructura y Sistemas de Transporte Maestría en Ingeniería – Geotecnia Doctorado en Ingeniería - Ingeniería Civil

Mayor información:

E-mail: asisacic\_med@unal.edu.co Teléfono: (57-4) 425 5172